

Components and catalysts for the polymerization of olefins.

Patent
Number: EP0045975

Publication
date: 1982-02-17

Inventor(s): PARODI SANDRO; NOCCI ROBERTO; GIANNINI UMBERTO DR; BARBE PIER CAMILLO DR; SCATA UMBERTO

Applicant(s):: MONTEDISON SPA (IT)

Requested
Patent: EP0045977 ✓

Application
Number: EP19810106299 19810813

Priority
Number(s): IT19800024141 19800813

IPC
Classification: C08F10/00 ; C08F4/64 ; C08F4/02

EC
Classification: C08F10/00

Equivalents: AU552621, AU557334, AU559388, AU7397181, AU7397281, AU7397381, BR8105185, BR8105189, BR8105190, CA1174225, CA1185960, CA1185961, CS226436, CS226437, DE3175804D, DE3177032D, DE3177124D, DE3177262D, DK160256B, DK160256C, DK163248B, DK163248C, DK164878B, DK164878C, DK349681, DK349781, DK349881, EP0045976, EP0223010, ES8300794, ES8300795, ES8300796, FI70028B, FI70028C, FI70029B, FI70029C, FI70030B, FI70030C, FI812440, FI812441, FI812442, HU186397, HU186399, HU186400, IN154219, IN154898, IN155867, IT1209255, JP1891973C, JP1950679C, JP1962732C, JP1997565C, JP2005187C, JP2500297B2, JP2500298B2, JP2647625B2, JP2647626B2, JP2749799B2, JP3038285B, JP3115310, JP4006724B, JP4075245B, JP4080044B, JP4348110, JP4348111, JP57063310, JP57063311, JP57063312, JP6070097B, JP6293804, JP6293806, JP7002921, JP7002926, JP7005662B, JP9202808, KR8400802, KR8400803, KR8400804, MX159065, MX159066, MX159151, NO159282B, NO159282C, NO159283B, NO159283C, NO160303B, NO160303C, NO812675, NO812676, NO812677, PH17748, PH17760, PH17763, PL232574, PL232575, PL232576, PT73499, PT73500, PT73501, RU2111975, SG33087G, SU1457813, SU1568890, YU195781, YU195881, YU195981, ZA8105487, ZA8105491, ZA8105496

Abstract

Catalysts for the polymerization of alpha-olefins which comprise the reaction product of: a) an Al-alkyl compound; b) a silicon compound containing at least one Si-OR or Si-OCOR or Si-NR₂ bond, R being a hydrocarbyl radical; c) a solid comprising as essential support, a Mg dihalide in active form and supported therein a Ti halide or a halo-Ti-alcoholate or said halogenated Ti compound and a silicon compound as defined in b) in a molar ratio with the supported Ti compound from 0,1 to 5 mole of silicon compound per mole of Ti compound.

Data supplied from the esp@cenet database - I2